

Biocompatibility product Information

Page 1 / 1

Product: Ultrafuse® PLA PRO1

Revision: 6/7/2022 Version: 1.2

Contact:

BASF 3D Printing Solutions B.V. Eerste Bokslootweg 17 7821 AT Emmen, The Netherlands sales@basf-3dps.com www.forward-am.com

Ultrafuse® PLA PRO1 material is 3D printed as test specimens and <u>successfully passed</u> the requirements of the stated tests below:

- Cytotoxicity XTT Test Neutral red (ISO 10993-5:2009)
 The extract of the product Ultrafuse® PLA PRO1 resulted in a cell vitality of more than 70% in comparison to the negative control and can therefore be considered to be not cytotoxic.
- Skin Irritation Test (ISO10993-10:2013)
 All 10 volunteers exhibited no dermal changes in the test zone at 24h, 48h and 72h when exposed to Ultrafuse® PLA PRO1.
- Skin Sensitisation Test Local Lymph Node Assay KretinoSens (ISO10993-10:2020)
 The extracts of the product Ultrafuse® PLA PRO1 resulted in an induction of the luciferase activity of less than 1.5 times compared to the DMSO control and is therefore to be assessed as non-sensitizing.

The performed biocompatibility tests were recorded on test specimen of the above referenced product to show compatibility of the material in general. The biocompatibility tests listed are not part of any continuous production protocol. The test assessments reflect only the test specimen and have to be retested on the final product. It remains the responsibility of the device manufacturers and/or endusers to determine the suitability of all printed parts for their respective application.

Fornotice:

We give no warranties, expressed or implied, concerning the suitability of above-mentioned product for use in any medical device and pharmaceutical applications.

All information contained in this document is given in good faith and is based on sources believed to be reliable and accurate at the date of publication of this document.

It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed. The certificate is exclusively for our customers and respective competent authorities. It is not intended for publication either in printed or electronic form (e.g. via Internet) by others. Thus, neither partial nor full publication is allowed without written permission.

This product information was generated electronically and is valid without signature.