

# HARZ Labs Dental Pink

Material Technical Data Sheet (TDS)

Version 1.1 / EN 16 April 2020



## SECTION 1: DESCRIPTION AND APPLICATION

Dental Pink resin is PMMA-like resin, made of biocompatible raw materials, with gum semitransparent color. Recommended for printing of dental model of gum color such as Gingiva mask.

## **SECTION 2: MATERIAL PROPERTIES**

### 2.1 Characteristics of liquid

Tested property	Standard/Method	Result (Metric)	Result (Imperial)
Color	-	Pink (semitransparent)	
Odor	-	Odorless	
Density	ASTM D1298	$1.1\mathrm{g/cm}^3$	0.0397 lb/in <sup>3</sup>
Viscosity (20 °C)	ASTM D2393	1.5 Pa∙s	1.008 lb/ft·s

## 2.2 Mechanical properties

Tested property	Standard/Method	Result (Metric)	Result (Imperial)
Flexural Strength	ASTM D790	103.8 ± 3.2 MPa	15.1 ± 0.5 ksi
Flexural Modulus	ASTM D790	2110 ± 80 MPa	306 ± 12 ksi
Ultimate Tensile Strength	ASTM D638	65.1 ± 2.1 MPa	9.4 ± 0.3 ksi
Elongation at Break	ASTM D638	6.8 ± 2.1 %	
Hardness	ASTM D2240	82 ± 3, Shore D	
IZOD Impact (Unnotched)	ASTM D4812	$6.4 \pm 1.0 \text{ kJ/m}^2$	3.1 ± 0.5 ft-lb/in <sup>2</sup>

#### 2.3 Special parameters

Tested property	Standard/Method	Result
Solubility (24h)	ASTM D3132	≤ 0.01%
Sorption (24h)	ASTM D570	≤ 0.47 %
Free Monomer Extraction	ISO 10993	Passed
Cytotoxicity	ISO 10993	Passed
Irritation	ISO 10993	Passed
Sensitization	ISO 10993	Passed

The information above is believed to be accurate and represents the best information currently available to us. The Imperial values are converted from Metric measurements and are for reference only. All test specimens were printed, cleaned, and post-processed per instructions provided by HARZ Labs company. Results provided here are representative of these processes and may vary if these established protocols are not followed. Users should make their own investigations to determine the suitability of the information for their particular purposes. In no event shall HARZ Labs LLC (OOO «XAPLI Лабс») be liable for any claims, losses, or damages of any third party or for lost profits or any special, indirect, incidental, consequential or exemplary damages, howsoever arising, even if HARZ Labs LLC (OOO «XAPLI Лабс») has been advised of the possibility of such damages.