

TECHNICAL DATA SHEET Silicon Carbide Filamet™

Physical Properties	Unit	Value
Density	g/cc	1.9
Humidity Absorption	%	No information available
Tensile Strength	MPa	No information available
Tensile Elongation	%	No information available
Flexural Strength	MPa	No information available
Flexural Modulus	GPa	No information available
Izod Impact Strength	kJ/m²	No information available

SECTION 2 - FILAMENT SPECIFICATION

Nominal Diameter	Diameter Tolerance	Ovality
1.75mm	± 0.05	≥ 95%
2.85mm	± 0.05	≥ 95%

Net Filament Weight Silicon Carbide Content

500/250 grams 67.6%

SECTION 3 - GUIDELINE FOR PRINT SETTINGS

Advised Printing Temperature 205-235°C

Advised Build Plate Temperature 40-50°C

Build Plate Surface Type Glass//PEI/Fiberglass/Spring Steel

Build Plate Preparation Glue Stick (on glass) Blue Painter's Tape (on PEI/Fiberglass) - Nothing needed for Spring

Steel

Print Cooling None

Advised Printing Speed 60mm/sec (3600mm/min)

Nooze Size/Type 0.6mm/Hardened Steel

SECTION 4 - ADDITIONAL INFORMATION

This filament is abrasive and will wear standard brass nozzles fast. The Virtual Foundry, Inc recommends a hardened steel nozzle.

DISCLAIMER: The product and technical information provided in this datasheet is correct to the best of The Virtual Foundry, Inc's knowledge. The information given is provided as a guidance for good use, handling and processing and is not to be considered as a quality specification. The information only relates to the specific product and the material properties.