

**SECTION 1 - TYPICAL MATERIAL PROPERTIES**

<b>Physical Properties</b>	<b>Unit</b>	<b>Value</b>
Density	g/cc	3.0
Humidity Absorption	%	No information available
Tensile Strength	MPa	No information available
Tensile Elongation	%	No information available
Flexural Strength	MPa	No information available
Flexural Modulus	GPa	No information available
Izod Impact Strength	kJ/m <sup>2</sup>	No information available

**SECTION 2 - FILAMENT SPECIFICATION**

<b>Nominal Diameter</b>	<b>Diameter Tolerance</b>	<b>Ovality</b>
1.75mm	± 0.05	≥ 95%
2.85mm	± 0.05	≥ 95%

  

<b>Net Filament Weight</b>	<b>Metal Content</b>
1000/500 grams	70%

**SECTION 3 - GUIDELINE FOR PRINT SETTINGS**

Advised Printing Temperature	205-235°C
Advised Build Plate Temperature	40-50°C
Build Plate Surface Type	Glass//PEI/Fiberglass/Spring Steel
Build Plate Preparation	Glue Stick (on glass) Blue Painter's Tape (on PEI/Fiberglass) - Nothing needed for Powder Coated Spring Steel
Print Cooling	None
Advised Printing Speed	60mm/sec (3600mm/min)
Nooze Size/Type	0.6mm/Stainless Steel or harder

**SECTION 4 - ADDITIONAL INFORMATION**

**Sintering Temperature:** 1200-1400°C (2192-2252°F)

This filament is abrasive and will wear standard brass nozzles fast. The Virtual Foundry, Inc recommends a stainless steel or hardened steel nozzle. A Filawarmer is required for this filament.

**DISCLAIMER:** The product and technical information provided in this datasheet is correct to the best of The Virtual Foundry, Inc's knowledge. The information given is provided as a guidance for good use, handling and processing and is not to be considered as a quality specification. The information only relates to the specific product and the material properties.