

PRELIMINARY TECHNICAL DATA SHEET

Tarfuse® POM

Filaments 3D

Version No.: 1.1
Date: 04.2021

General Information

CHARACTERISTICS

Tarfuse® POM is made of polyacetal copolymer, characterized by high mechanical strength, excellent tribological parameters. Tarfuse® POM is designed for printing functional technical parts, due to the material features dedicated to printing parts up to 100mm.

APPLICATIONS

Tarfuse® filament for Fused Filament Fabrication.

DELIVERY FORM

Tarfuse®: diameter 1,75±0,05mm

PACKAGING

Packing available: 1kg +(250 g spool)

COLOUR

Natural, black

STORAGE

Tarfuse® POM filament must be stored in closed original packaging of the producer in dry rooms. Protect the packaging's against damage and against the influence of weather conditions.

DRYING RECOMMENDATIONS

To ensure good print quality, it is recommended to dry in a hot air dryer for 4 to 6 hours in 140°C

NOTICE

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

PRELIMINARY TECHNICAL DATA SHEET

Tarfuse® POM

Filaments 3D

Version No.: 1.1
Date: 04.2021

RECOMENDED PRINT PROCESSING PARAMETERS

Nozzle temperature: 210 - 240 °C

Build chamber temperature: 70 - 140 °C

Bed temperature: 100 - 130 °C

Bed material: PI + Dimafix, cellulose mat (paper, wood, cork) + PVA adhesive

Nozzle diameter ≥ 0,4 mm

Print speed: 10-30 mm/s (slowly)

Physical Properties	Unit	Data	ISO standard	Test conditions
Melting temperature; DSC	°C	165-170 °C	11357-1-3	10°C/min.
Glass transition temperature; DSC	°C	-50 °C	11357-1-3	10°C/min.
Crystallization temperature; DSC	°C	140	11357-1-3	10°C/min.
Density	g/cm ³	1,42	1183	-
Humidity absorption	%	0,2	62	23°C/50%RH
Water absorption	%	0,8	62	23°C/sat.
Melt volume-flow rate MVR	cm ³ /10min	2,5	1133	275°C/5 kg

Mechanical Properties	JM	XY	XZ	ZX	ISO standard	Test conditions
Print direction		Flat	On its edge	Upright		
Tensile strength	MPa	50	To be tested	To be tested	527-1,-2	50mm/min
Elongation at break	%	11	-	-	527-1,-2	50mm/min
Tensile E-modulus	MPa	1870	-	-	527-1,-2	1mm/min
Flexural strength	MPa	-	-	-	178	2mm/min
Flexural modulus	MPa	-	-	-	178	2mm/min
Charpy impact strength	kJ/m ²	-	-	-	179-1	1eU
Charpy notched impact strength	kJ/m ²	-	-	-	179-1	1eA
Vicat softening point	°C	-	-	-	306	50N
Heat deflection temperature	°C	-	-	-	75-1,-2	1,8 MPa

Print processing parameters:

Nozzle temperature 230 °C
Build chamber temperature 70 °C
Bed temperature 130 °C
Bed material PI + Dimafix
Nozzle diameter 0,4 mm
Layer 0,2 mm
Filling 100%; 45°/45°

Tests were performed at 23 °C, unless otherwise specified.